

# Wood Species

Wood has its own natural characteristics and materials may vary from product samples and printed materials. We cannot warrant against natural variations or the differences between the color grain and appearance of product samples.



**CURLY MAPLE**

*Janka: 1450*



**MAPLE**

*Janka: 1450*



**ASH**

*Janka: 1320*



**POPLAR**

*Janka: 540*



**YELLOWHEART**

*Janka: 1820*



**HICKORY**

*Janka: 1820*



**QTR. RED OAK**

*Janka: 1290*



**PLN. RED OAK**

*Janka: 1290*



**QTR. WHITE OAK**

*Janka: 1360*



**PLN. WHITE OAK**

*Janka: 1360*



**AMERICAN CHERRY**

*Janka: 950*



**GEN. MAHOGANY**

*Janka: 800*



**ZEBRAWOOD**

*Janka: 1575*



**TIGERWOOD**

*Janka: 2620*



**SAPELE**

*Janka: 1439*



**MERBAU**

*Janka: 1654*




**BRAZILIAN CHERRY**

*Janka: 2350*



**BUBINGA**

*Janka: 1980*




**PADAUK**

*Janka: 1725*



**CUMARU**

*Janka: 3540*




**SANTOS MAHOGANY**

*Janka: 2200*




**BLOODWOOD**

*Janka: 2900*




**JARRAH**

*Janka: 1910*



**SIPO**

*Janka: 1260*



**LEOPARDWOOD**

*Janka: 840*




**QTR. AMER. WALNUT**

*Janka: 1010*




**PLN. AMER. WALNUT**

*Janka: 1010*




**IPE**

*Janka: 3060*



**PURPLEHEART**

*Janka: 2090*



**WENGE**

*Janka: 1630*

## JANKA WOOD HARDNESS RATING

The Janka measures measures the ability of a wood species to withstand denting and wear. The higher the number, the greater the required force. It It also indicates how hard or easy a species is to saw or nail.

